









colors



Athenian / ALASKA GLACIER




Athenian / RENOIR




Athenian / CALACATTA GOLD


Classic and enduring, tile that captures the beauty of Italian marble. The Athenian collection is a tribute to the high-end appearance of marble. Exceptional in both look and quality, Athenian is engineered for applications where elegance is desired.














Athenian / ALASKA GLACIER





















Athenian / CALACATTA GOLD











SIZES & SHADE VARIATION

22

sizes:

12"x24"

Pressed/Matte

1101490 Alaska Glacier

1101491 Renoir

1101492 Calacatta Gold

mosaics & trim pieces: 12"x12"

Mosaic matte 2"x2"



1101502 Alaska Glacier

1101503 Renoir

1101504 Calacatta Gold

3"x24"Bullnose matte



1101499 Alaska Glacier 1101500 Renoir 1101501 Calacatta Gold



UNIFORM

APPEARANCE

Differences among pieces from the same production run are minimal.



SLIGHT VARIATION Clearly distinguishable differences in texture and/or pattern with similar colors.



While the colors present on a single piece of tile will be indicative of the colors to be expected on the other tiles, the amount of colors on each piece will vary significantly.



SUBSTANTIAL VARIATION

Random color differences from tile to tile, so that one tile may have totally different colors from that on other tiles. Thus, the final installation will be unique.

Technical Specifications

This product meets or exceeds all standards described in ANSI A137.1 & A137.3. Este product cumple o exceed todos los estandares de ANSI A137.1 & A137.3.

	SPECS	TEST METHOD	INDUSTRY STANDARD	MILE®stone VALUES	
	WATER ABSORPTION	ASTM C373	≤0.5%	≤0.5%	
*	SURFACE WEAR RESISTANCE	ANSI A137.1	Surface Wear-resistance properties of glazed vitreous and porcelain tiles.	ALL RESIDENTIAL / COMMERCIAL	
^	CHEMICAL RESISTANCE	ASTM C650	A tile sample is placed in continuous contact with a variety of chemicals for 24 hours. Sample must show no visible defects.	NOT AFFECTED	
*	D.C.O.F. AcuTest®	ANSI A326.3	INDOOR ≥0.42 WET OUTDOOR >0.55 WET	≥0.42 WET >0.55 WET 2CM & GRIP	
*	STAIN RESISTANCE	ASTM C1378	Surfaces are exposed to staining agents for 24 hours followed by four cleaning procedures. Results are recorded post cleaning.	NOT AFFECTED	
	BREAKING STRENGTH GAUGED PORCELAIN	ASTM C1505	≥175 lbf	≥200 lbf	
<u> </u>	BREAKING STRENGTH	ASTM C648	≥275 lbf	≥300 lbf ≥2500 lbf	
	BREAKING STRENGTH OUTDOOR 2CM	ASTM 1505	2000 lbf (10.9 kN)		
*	RESISTANCE TO FREEZE	ASTM C1026	A tile sample is subjected to repeated processes of freezing and thawing. Sample must show no visible defects.	RESISTANT	
	WARPAGE EDGE	ASTM C485	±0.40% or ±0.05 in (±1.8 mm)	± 0.40%	Rectified
	WARPAGE DIAGONAL	ASTM C485	±0.40% or ±0.07 in (±1.8 mm)	± 0.40%	Rectified
H	WEDGING	ASTM C502	±0.25% or ±0.03 in (±0.8 mm)	± 0.25%	Rectified
	WARPAGE EDGE	ASTM C485	±0.50% or ±0.07 in (±1.8 mm)	± 0.50%	Calibrated
	WARPAGE DIAGONAL	ASTM C485	±0.50% or ±0.07 in (±1.8 mm)	± 0.50%	Calibrated
<u></u>	WEDGING	ASTM C502	±0.50% or ±0.08 in (±2.0 mm)	± 0.50%	Calibrated
<u> </u>	THICKNESS	ASTM C499	Range: ± 0.04 in	≤0.04 in	

[•] Due to the inherent nature of fired porcelain tile, it is important to note that the coefficent of friction may vary within and between product runs.



35-02 Northern Boulevard, Long Island City, N.Y. 11101 www.hometilecenterofny.com (718) 361-9401